

---

<b>Product name</b>	:	<b>Filler Spray</b>
<b>Article number</b>	:	<b>33 870</b>
<b>Exclusive Distributor</b>	:	<b>Fournarakis S.A.</b>
		<b>9.5 klm Attiki Odos exit 4 Aspropyrgos Athens Greece</b>
		<b>Telephone number + 30 210 55 98 400</b>
		<b>Telefax number + 30 210 55 98 440</b>
		<b>Made in Holland</b>

---

### Product description

High quality, fast-drying filler to fill small irregularities in surfaces, treated and untreated, of wood, metal and aluminium.

Suitable primer as pre treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers).

### Product characteristics

Fast drying  
Excellent coverage  
Corrosion preventive  
Easy to sand, both wet and dry (from grain 400)  
Excellent filling property  
Good adhesion  
Re-sprayable with all lacquer systems

### Physical and Chemical Characteristics

Contents	:	400ml
Base	:	Acrylic resin
Colour	:	Beige-yellow
VOC-content	:	Approximately 75% w/w
Solid content	:	Approximately 25% w/w
Coverage	:	1,25 to 1,75 m <sup>2</sup>
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 2 hours
Heat resistant	:	To 110°C



### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

#### Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

#### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the filler in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**